

TECHNICAL DATA SHEET

04.03.2025

Version 4.4

SULAPAC BARRIER – BA2002.0NC

Sulapac Barrier is a sustainable solution for injection molding. Designed to be used as the inner layer of a cosmetic jar, Sulapac Barrier provides excellent barrier properties against water evaporation making it ideal for water-based cosmetics. It can be use in both bi-injection (2K jars) or 4 part molds.

TYPICAL MATERIAL PROPERTIES	
	BA2002.0NC
PHYSICAL PROPERTIES	
Hardness (Shore D)	85
Material density (g/cm ³)	1,49
Shrinkage (%)	1
TENSILE PROPERTIES (ISO 527-1)	
Tensile strength at yield (MPa)	44
Tensile modulus (GPa)	8,7
Tensile strain at yield (%)	1,1
FLEXURAL PROPERTIES (ISO 178)	
Flexural strength at max load (MPa)	65
Flexural modulus (GPa)	8,2
Flexural strain at max load (%)	1,1
IMPACT PROPERTIES (Unnotched, ISO 179-1)	
Charpy impact strength (kJ/m ²)	9
RHEOLOGICAL PROPERTIES (ISO 1133) (190°C/2,16 kg)	
MFI (g/10min)	12
HEAT RESISTANCE	
HDT-B (°C)	150
BIOBASED CONTENT (ASTM D6866)	
Biobased content (%)	98

BARRIER PROPERTIES

WVTR (23 °C/85%) (g/m ² /day)	0,01
OTR (23 °C/0%) (cm ³ /m ² /day)	2,3

WVTR = water vapor transmission rate (ASTM F1249)

OTR = oxygen transmission rate (ASTM D3985)

DRYING AND MASTERBATCH INSTRUCTIONS

DRYING

- Before processing, the granules should be dried using a dehumidifying dryer or a vacuum dryer
 - Dehumidifying dryer: the granules should be dried for at least 5-6 hours at 80 °C
 - Vacuum dryer: the granules should be first dried for at least 20 minutes at 80 °C
- The best end result will be achieved if the residual moisture of the granules is < 0,2 %
- After drying, avoid exposing the material to ambient conditions
- Moisture content can lead to hydrolysis

MASTERBATCH

- Sulapac materials can be colored in the same way as conventional plastics. With Sulapac materials use color masterbatches with biodegradable carriers; PLA, PHA, PBAT, PBS. For further information, please see Sulapac color masterbatch guide.
- If adding color masterbatch, ensure the granules have cooled down to 50 °C after drying to avoid the agglomeration of color masterbatch granules

PROCESSING CONDITIONS

GENERAL INSTRUCTIONS

- Typical settings may require optimization
- Material has a relatively narrow processing window (sensitive to temperature adjustments), thus correct processing parameters must be ensured
- Both cold and hot runner systems are suitable for these materials
- Valve gate systems can be used
- Tool temperature must be kept at given temperature range to secure barrier properties and easy ejection of the final part

RECOMMENDED TEMPERATURES

Throat	40 - 60 °C
Feed zone	165 °C
Compression zone	175 °C
Homogenizing zone	180 °C
Machine nozzle	180 °C
Back pressure	5 - 10 bar
Hot runner nozzle and bushing	180 - 183 °C
Tooling temperature	60 - 70 °C

PURGING INSTRUCTIONS

BEFORE PRODUCTION

- Purge the plasticization unit and the hot runner with PP or PE

DURING PRODUCTION

- The material is heat sensitive. Avoid high processing temperatures and long dwell times
- If an extensive amount of burned material or fumes starts to appear in the products, try lowering processing temperature
- In case of production break flush the plasticization unit with fresh material

AFTER PRODUCTION

- Purge the plasticization unit and the hot runner with PP or PE
- Clean up the mold after production

STORAGE, TRANSPORTATION AND SHELF-LIFE

STORAGE

- In original unopened packaging at temperatures below 45 °C
- Once opened, reseal the package after each use
- In dry conditions and avoid exposure to high humidity and rain
- Away from direct sunlight

TRANSPORTATION

- Temperatures during transportation may not exceed 60 °C

SHELF-LIFE

- Shelf-life is from the date of manufacture, for unopened bags at room temperature (23 °C)
- Date of manufacture can be found on the label attached to the original packaging

Sulapac Barrier – BA2002.0NC

18 months

The information provided in this safety data sheet is based on our current knowledge and experience at the date of its publication and describe the material only with regards to safety requirements. No representation or warranty is made as to the truth or accuracy of any data, information or opinions contained herein or as to their suitability for any purpose, condition, or application. The information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. It is the responsibility of the recipient of the product to ensure any proprietary rights and existing laws and legislation are observed.



Sulapac is proud to be an ISO 9001 and ISO 14001 certified company.